



# ANTIROUILLE MINIMUM GRIS

Primer for metal

## DESCRIPTION

It's a fast drying, alkyd based primer.

## FIELD OF USE

Very good primer for metal (iron and steel-work) free from rust and grease.

Well appreciated for all types of metal work including agricultural material, industrial boilers and buildings, etc....

Protects against rust after the surface has been mechanically cleaned, eliminating the rust layer formed on the surface.

## TECHNICAL CHARACTERISTICS

- Aspect : Matt Satin finish.
- Color : Grey.
- Spreading-rate : 7 to 9 m<sup>2</sup>/Kg.
- Density : 1.53 +/- 0.05 Kg/L at 25°C.
- % Solids (by weight) : 81 +/- 2 %.
- Viscosity : 105 KU +/- 5 with the Krebs Stormer at 25°C.

## APPLICATION PROPERTIES

Normal application is by brush. The roller can be used for the second coat. Avoid applying by spray. If spray application is necessary, use a solvent vapour resistant safety mask.

The performance of the coating depends upon a good surface preparation.

For easy application and optimum performance the surface needs to be clean, sound, dry and smooth before rendering. Do not apply in wet conditions, with temperatures below 5°C and/or relative humidity over 70%.

## APPLICATION DETAILS FOR USAGE

Dilution : D66 (White Spirit)

## DRYING TIME

- \* Touch dry : 4 hours.
  - \* Through dry : 12 hours/
  - \* Recoat time : minimum 24 hours.
- Applied film thickness by coat (in microns) :
- \* Dry : 35 to 50 μ
  - \* Wet : 70 to 100 μ (two coats)

## STORAGE

Nine months in the closed paint can, as delivered. Store inside in conditions avoiding extremes of hot and cold temperatures. Keep away from sources of heat, sparks and flames.

## PACKAGING

1kg, 5 Kg and 30 Kg

## HEALTH & SAFETY

Flammable use only in well ventilated areas. Dangerous if inhaled and /or if left in contact with the skin. For more details, consult safety data sheet N° 41.