



DESCRIPTION

Quick drying alkyd primer for iron and ferrous alloys, example of rust and grease.

FIELD OF USE

Used for metal frames, agricultural equipment, locksmiths, industrial and building boilermaking, etc. The Gray Rustproofing agent performs the function of rust remover after mechanical brushing to remove the layer of rust formed.

TECHNICAL CHARACTERISTICS

- Aspect : Velvety mat.
- Grey color.
- Spreading-rate : 7 à 9 m²/Kg.
- Density: 1,57 +/- 0,05 at 25°C.
- Dry extract by weight : 81 +/- 2 %.
- Viscosity : 105 +/- 5 KU with a Krebs viscometer at 25 ° C.

SURFACE PREPARATION

The work must be done in accordance with standard NF DTU59.1 and will be carried out with the greatest care.

CONDITIONS AND METHODS OF APPLICATION

Mainly the brush. The roller can be used for a second coat. Do not apply on condensing or frozen substrates at temperatures below 5 ° C, nor at relative humidity above 70%.

APPLICATION DETAILS OF USAGE

Dilution : D66 (White Spirit)

DRYING TIME

- * Dry without dust: 1 hour.
 - * Dry to touch: 6 hours.
 - * Recovery time: 24 hours minimum.
- Film thickness per layer in microns:
- * Dry: 35 to 50 µm.
 - * Wet: 70 to 100 µm (two coats).

STORAGE

The product can be stored for up to 2 years in good storage conditions away from sunlight and frost in its original closed packaging. It is nevertheless recommended to shake the product before use.

PACKAGING

1kg, 5 Kg.

HEALTH & SAFETY

Health and safety information and precautions for use are detailed in the safety data sheet N °41.

Edition : July 2020 by Colorado 07/20 (DC28 D).

N.B : The purpose of this technical data sheet is to provide information on the properties of our product. The information contained therein is based on our current knowledge of tests carried out with a constant concern for objectivity according to the conditions of use in accordance with standards or DTU in force; However, the information cannot replace an appropriate description and the state of the funds to be painted. This descriptive technical sheet cancels and replaces any sheet relating to the same product. The above technical data does not imply acceptance of the guarantees. Close the pot tightly after use. Help preserve the environment by not disposing of waste in the drains or household waste. Please return your empty jar to a recycling center. For your unused product, please contact your local authorities for information on disposal and collection.

COLORADO is certified ISO 9001, ISO 14001 and ISO 45001