



DESCRIPTION

Fast drying alkyd primer for iron and ferrous metals, free from rust and grease.

8,7>6 A8GE7

Suitable for metal frames, agricultural equipment, locksmiths, industrial boilermaking, etc.

F75: @;53>5: 3D35F7D;EF;5E

- Aspect : Satin.
- Color: Red brown.
- Spreading-rate : 8 to 10 m²/Kg, Complies with ISO 23811 (2009).
- Density : 1,55 +/- 0,05 at 25°C, Complies with NM ISO 2811-1 (2008).
- Dry extract by weight : 77 +/- 2 %.
- Viscosity : 105 +/- 5 KU with a Krebs viscometer at 25 °C.

EGD8357 BD7B3D3F;A@

The work must be done in accordance with standard NF DTU59.1 and will be carried out with the greatest care.

5A@6;F;A@E 3@6 ? 7F: A6E A83BB>53F;A@

Usually the brush. The roller can be used for a second coat. The gun should be avoided. If requested, a respiratory mask should be worn. Minimum brushing. The performance of the coating is a function of the surface preparation.

Application limit: Do not apply on condensing or frozen substrates at a minimum temperature of 8 °C and a maximum of 35 °C. HR <70%.

3BB>;53F;A@67F3;>E A8GE397

Dilution : D66 (White Spirit)

6DK;@9 F;? 7

- * Dry outside: 1 hour.
 - * Dry to touch: 6 hours.
 - * Hard to heart: 12 hours.
 - * Recovery time: 24 hours minimum.
- Film thickness per layer:
- * Dry: 35 to 50 µm.
 - * Wet: 70 to 100 µm (two coats).

EFAD397

The product can be stored for up to 1 year in good storage conditions away from sunlight and frost in its original closed packaging. It is nevertheless recommended to shake the product before use.

B35=39;@9

1kg, 5 Kg, 30 Kg

: 73>F: ~ E387FK

Health and safety information and precautions for use are detailed in the safety data sheet N° 41.

Edition : November 2020 by Colorado 11/20 (DC28 D).

N.B : The purpose of this technical data sheet is to provide information on the properties of our product. The information contained therein is based on our current knowledge of tests carried out with a constant concern for objectivity according to the conditions of use in accordance with standards or DTU in force; However, the information cannot replace an appropriate description and the state of the funds to be painted. This descriptive technical sheet cancels and replaces any sheet relating to the same product. The above technical data does not imply acceptance of the guarantees. Close the pot tightly after use. Help preserve the environment by not disposing of waste in the drains or household waste. Please return your empty jar to a recycling center. For your unused product, please contact your local authorities for information on disposal and collection.

COLORADO is certified ISO 9001, ISO 14001 and ISO 45001