



DESCRIPTION

It is designed for the penetration and waterproofing of floury masonry substrates (plaster, cement, lime), before the application of paints and facade coatings. The application of Coloprime increases the performance of vinyl paints. Part of the generation of selective waterproofers because it acts as a barrier to runoff and infiltration water while allowing the support to breathe. Classification NM 03.3.009 Family I, 7b2.

FIELD OF USE

Recommended for application on exterior and interior masonry walls.

TECHNICAL CHARACTERISTICS

- Aspect : Satin.
- Colors: Transparent.
- Spreading-rate:
 - * On cement plaster : 8 to 10 m²/L.
 - * On Concrete : 15 to 20 m²/L depending on the porosity of the support.
- Density : 1,01 ± 0,05 at 25°C.
- Dry extract (by weight): 14 % +/- 2%.
- Viscosity : 15 ± 5 seconds CF4 at 25°C.

SURFACE PREPARATION

The work must be done in accordance with standard NF DTU59.1 and will be carried out with the greatest care.

CONDITIONS AND METHODS OF APPLICATION

Apply with a roller or brush.
Application limit: Do not apply on substrates condensing or frozen at temperature below 7 ° C, nor at relative humidity above 70%.

APPLICATION DETAILS OF USAGE

Dilution: Running water.

DRYING TIME

Drying at 20 ° C and 60% humidity:
*Dust dry: 20 min.
*Dry: 1 hour.
*Recoat: 2 hours.

STORAGE

The product can be stored for up to 2 years in good storage conditions away from sunlight, it is nevertheless recommended to shake the product before use.

PACKAGING

1L, 5L, 20L.

HEALTH & SAFETY

Health and safety information and precautions for use are detailed on the safety data sheet N° 62.

MINIMUM ORDER QUANTITY

100 kg

7/1/2018, December 2018 Tk 5a'adSva #2!\$ /65\$*9fz

@Z4, FZVbgbaeWAXfZ[efVWZ` [US^VSFSzVWV[efabdh[VWV` Xad_Sf[a` a` fZWbcbVWV[efaxagdbbVgUfZFWV` Xad_Sf[a` Ua` fS` W fZWVWV[efTSeWV a` agdUgdVf]` ai` WYVWAXfVWV[efUSdVW agfi [fZ SUa` eS` fUa` UWV XadaTWV[h]rkSUadV[Y fa fZWUa` V[f[a` eaXgeWV` SUad/S` UW [fZ eS` VSD/ead6FG [XadUW : ai` VVWd fZWV` Xad_Sf[a` US` af dVW` SUMS` SbbdbbqSfWVWV[h]bf[a` S` V fZWVWVWAXfZWVg` Vefa TWbS[fVWz FZ[efVWU[h]bf[hVWVWZ` [US^ezVWV US` UWeS` V dVW` SUMS` k eZVWV dVWV[Y fa fZWVW` VbcbVgUfZFWVSTahVWVWZ` [US^VSFSVaVW` af [b'k SUUWbS` UWAXfZWVgSd` fVWz 5^aeWZVWbaf f[YZf'k SXVdgelV: VbcbVWVWVWVWV[h]da` _ WfTk` af V[ebae] Y aXi SefV[fZWVWdS` eadZagelZa` Vi SefVZBVSedVWgd kagdW` bfk Sdfa S dVWUf Y UW fVWZ8adkagdg` geWV bcbVgUf bVWVWUa` fSUF kagd'atUS^SgfZad[fVW` Xad` Xad_Sf[a` a` V[ebaeS`S` V Ua` VVWV[a` z

5A>AD36A [eUWV[XWV;EA +""#1;EA #&"#1;EA &'""#S` V;EA \$)""#