



## COLOVINYL 600 EXTRA

Acrylic Matt paint for high quality  
EXTERIOR/INTERIOR



### DESCRIPTION

Matt paint based on an acrylic co-polymer, and natural fillers and pigments Titanium Dioxide, calcium carbonate, talc and water. This product also contains various additives in very small quantities, like dispersing and wetting agents, thickeners, defoamers, biocides and coalescing agents.

Conforms to the French Standard NF 36-005, Family I, Class 76.

### FIELD OF USE

Colovinyl 600 EXTRA can be applied on masonry, wood and plaster substrates. It has a high degree of whiteness, an easy application properties and excellent scrub resistance.

### TECHNICAL CHARACTERISTICS

- Aspect : Smooth, matt finish.
- Colors : White, can be tinted with Teintes 2000 colorants. Special colors are supplied for above 100 Kg commands
- Spreading-rate : 7 à 9 m<sup>2</sup>/Kg per coat depending upon the support porosity of .complies with ISO 23811 (2009).
- Density : 1.65 Kg/L ± 0,05 to 25°C. complies with NM ISO2811-1(2008).
- % Solids ( by weight ) : 74 ± 2%.
- Viscosity : 500 ± 50 Poises at 25°C with the BrookField.

### SURFACE PREPARATION

For easy application and optimum performance the surface needs to be clean, sound and dry before rendering :

- \*Sand with a sandpaper.
- \*Remove the dust.
- \*Sand vigorously with Chiendent brush.
- \*Wash with a water-jet if necessary.

### APPLICATION PROPERTIES

Colovinyl 600 Extra can be applied with a brush or a roller without any risk of wet-edge problems. Do not apply on cold wet walls below 5°C or conditions of high relative humidity (> 70%).

### APPLICATION DETAILS FOR USAGE

- Dilution:
- \* 1st coat 15 to 20 % with water
  - \* 2nd coat 10 % with water

Edition : MAI 2018 by Colorado (11/16). This version replaces all previous editions.

N.B : The changing needs of our customers as well as technical progress may lead us to change the characteristics of our products without notice and without liability.

### DRYING TIME

- Drying at 20°C and 60% of humidity
- \* Touch Dry : 15 mn
  - \* Through Dry : 30 mn.
  - \* Recoatable after 4 hours.

### RECOMMENDED SYSTEM (consult us)

#### ■ EXTERIOR

SYSTEM	NUMBER OF COATS
ENDUIT FACADE P20 (option)	1
COLOPRIM	1
COLOVINYL 600 EXTRA	2

#### ■ INTERIOR

SYSTEM	NUMBER OF COATS
COLOPRIM	1
COLENDUIT EXTRA B805 or SP88	2
COLOSTOP (Optional)	1
COLOVINYL 600 EXTRA	2

### STORAGE

Two years in the closed plastic container, as delivered. Store inside in conditions avoiding extremes of hot and cold temperatures..

### PACKAGING

1 kg, 5 kg, 10 kg, 30 kg and 50 kg.

### HEALTH & SAFETY

This product is not classified as dangerous under current regulations. For more details consult the safety data sheet N° 248.