TECHNICAL DATA SHEET :

COLOVINYL 600 EXTRA



DESCRIPTION

Matt paint based on acrylic copolymers for careful work. Family I, class 7b according to the NFT 36-005 standard.

FIELD OF USE

COLOVINYL 600 Extra can be applied to masonry, woodwork and plaster coverings. Colovinyl 600 Extra has good opacity, good whiteness

as well as great ease of application and good abrasion resistance.

TECHNICAL CHARACTERISTICS

- Aspect : Matt and Smooth.
- Color : Delivered in white, it can be tinted with our 2000 tints. Special tints are delivered for orders over 100 Kg.
- Spreading-rate : 7 to 9 m²/Kg per layer depending on the porosity of the substrate, in accordance with ISO 23811 (2009).
- Density : 1,69 ± 0,05 at 25°C, complies with NM ISO 2811-1 (2008).
- Dry extract (by weight) : $73 \pm 2\%$.
- Viscosity : 460 ± 50 poises at 25 ° C at Brookfield.

SURFACE PREPARATION

The work must be done in accordance with standard NF DTU59.1 and will be carried out with the greatest care.

CONDITIONS AND METHODS OF APPLICATION

COLOVINYL 600 EXTRA can be applied with a roller or brush without any risk of rework or seaming. Application limit: Do not apply on condensing or frozen substrates at temperatures below 5 $^{\circ}$ C and above 35 $^{\circ}$ C, nor at relative humidity above 80%.

APPLICATION DETAILS OF USAGE

Dilution:

- * 1st layer 15 to 20% water.
- * 2nd layer +/- 10% water.



DRYING TIME

At 20 ° C and 60% humidity: * Dust free: 15 min.

* Dry: 30 min.

Recoatable after 4 hours.

RECOMMENDED SYSTEM (Consult us)

EXTERIOR

SYSTEM	NUMBER OF COATS
ENDUIT FACADE P20 or P10	1
COLOPRIM or COLOFIX	1
COLOVINYL 600 EXTRA	2

INTERIOR

SYSTEM	NUMBER OF COATS
COLOPRIM or COLOFIX or FORMORAL (*)	1
COLENDUIT Extra B505 or SP88	2
COLOSTOP (Optionnel)	1
COLOVINYL 600 EXTRA	2

(*) Depending on the support.

STORAGE

The product can be stored for up to 2 years under good storage conditions away from sunlight, it is nevertheless recommended to shake the product before use.

PACKAGING

1 kg, 5 kg, 10 kg, 30 kg, 45kg.

HEALTH & SAFETY

Health and safety information and precautions for use are detailed on the safety data sheet N° 248.

Edition : October 2021 by Colorado 10/21 (DC28 D).

N.B: The purpose of this technical data sheet is to provide information on the properties of our product. The information contained therein is based on our current knowledge of tests carried out with a constant concern for objectivity according to the conditions of use in accordance with standards or DTU in force; However, the information cannot replace an appropriate description and the state of the funds to be painted.

This descriptive technical sheet cancels and replaces any sheet relating to the same product. The above technical data does not imply acceptance of the guarantees. Close the pot tightly after use. Help preserve the environment by not disposing of waste in the drains or household waste. Please return your empty jar to a recycling center. For your unused product, please contact your local authorities for information on disposal and collection.

COLORADO is certified ISO 9001, ISO 14001 and ISO 45001