



COLOSTAR

Alkyd gloss paint
INTERIOR

DESCRIPTION

It is a gloss paint based on glycerophthalic resin modified semi-gloss. COLOLAC can be applied on all the usual interior surfaces which have been well prepared (cement coating, wood and primed metal

FIELD OF USE

Recommended for cement walls, plaster roof and wood

TECHNICAL CHARACTERISTICS

- Aspect : Gloss.
- Colors : According to the colour card. its color have been studied based on current collections coating. Delivered in different colors which can be mixed. Tintable with COLOPATE
- Spreading-rate : 8 to 9 m²/Kg for a wet film thickness of 75 microns, depending upon the tint and the porosity of the substrate.
- Density : 1,35 Kg/L ± 0.05 à 25°C (White).
% Solids (by weight) : 72% ± 2%.
Viscosity : 100KU ± 5 à 25 °C to KREBS viscometer

SURFACE PREPARATION

For easy application and optimum performance the surface needs to be clean, sound and dry before rendering :

- * Sand vigorously with Chiendent brush.
- * Sand with sandpaper.
- * Dusting.
- * Wash with water-jet if necessary.

APPLICATION PROPERTIES

COLOLAC can be applied by roller, brush, or spray. On smooth wood and plaster, apply a printing coat of Formoral than tow coats of Cololac. On cement, one printing coat of Coloprime or Imprex, one coat of Enduitpat P66 or Colendui, one coat of Itomat or Colomat, and two coats of Cololac. Application limit : Do not apply on cold wet walls below 5°C or conditions of high relative humidity (> 70%)

APPLICATION DETAILS OF USAGE

Dilution : D66 (White Spirit).

DRYING TIME

Drying at 20°C et 60% of humidity :

*Touch dry : 1h30

*Dry : 6h.

Recordable in a minimum 24 h

RECOMMENDED SYSTEM

■ INTERIOR

SYSTEM	NUMBER OF COATS
COLOPRIM	1
COLENDUITPAT P66 or COLENDUIT	2
COLOMAT	1
COLOLAC	2

STORAGE

One year in the closed container, as delivered. Store inside in conditions avoiding extremes of hot and cold temperatures..

PACKAGING

0,5kg, 1 kg, 5 kg 15kg, 20 kg et 25kg.

HEALTH & SAFETY

Flammable and harmful product.

For more details, refer to data sheet Safety N° 12.