




ENDUIFLEX

Hydraulic powdered render for reating humidity



DESCRIPTION

Powdered render based on a hydraulic binder and special extenders and a special hydrophobic resin. Stops humidity (class W3). Lets the support breath.

FIELD OF USE

Designed for retouching and finishing work on interior/exterior masonry, wet or humid such as cement, concrete, bricks or stone. Repairs holes up to 1 cm thick.

TECHNICAL CHARACTERISTICS

- Aspect : Powder.
- Color : White.
- Spreading-rate : 1.5 Kg/m² by mm of thickness.

SURFACE PREPARATION

For easy application and optimum performance the surface needs to be clean, sound and dry before rendering :

- * Sand vigorously with Chiendent brush.
- * Sand with sandpaper.
- * Remove the dust.
- * Wash with a water-jet if necessary.

Remove any traces of algal or fungal growth before applying. Rinse if necessary with a fungicidal solution, then leave to dry before applying ENDUIFLEX.

APPLICATION PROPERTIES

Recommended hardware: coating knife/spatula.
Apply for 2 coats depending upon the desired film thickness.
Apply an even coat over the surface.
In order to obtain an efficient protection, apply at least 2 mm of thickness in a regular way.

Recommended system:

	Number of coats
* ENDUIFLEX	2 (2 mm minimum)
* COLOPRIM	1

Limitation of use : Do not apply on condensant or frozen support at temperature below 5°C, or above 40°C relative humidity above 70%.

APPLICATION DETAILS FOR USAGE

Water (approximately 30%). Mix well and leave for 15 minutes, then mix again before applying.

DRYING TIME

Drying at 20°C and 60% of humidity :
* Recoat : 24 hours.

STORAGE

One year in the closed original container. Store inside in conditions avoiding extremes of hot and cold temperatures.

PACKAGING

5 kg.

HEALTH & SAFETY

For more details, consult the safety data sheet N° 115.