



DESCRIPTION

Decorative coating for interiors with pearl and sandblasted effect.

FIELD OF USE

Recommended for application on interior walls.

TECHNICAL CHARACTERISTICS

- Aspect : Pearly and finely sanded
- Colors : According to our color chart.
- Spreading-rate : 10 to 12 m²/Kg (in 1 layers), in accordance with ISO 23811 (2009).
- Density : 1.28 ± 0.05 at 25° C, complies with NM ISO 2811-1 (2008).
- Viscosity : 1000 ± 200 poises (M6/10) at 25° C (Brookfield).

SURFACE PREPARATION

The work must be done in accordance with standard NF DTU59.1 and will be carried out with the greatest care.

CONDITIONS AND METHODS OF APPLICATION

The substrate is prepared using a layer of Colofondo and let dry for 12 hours.
Apply SYLVIA using a flat brush (Spalter) in small alternating strokes on surfaces that do not exceed 2 m² in order to avoid rapid drying during application. Using a flat brush (Spalter), draw according to the desired finish (Diagonal, horizontal, circular or others). Application limit: Do not apply on condensing or frozen substrates, at temperatures below 5 ° C and above 35 ° C, or at relative humidity above 70%.

APPLICATION DETAILS OF USAGE

Dilution: ready to use. (Can be diluted up to 10% water).
Mix the product well with a spatula before use.

DRYING TIME

Drying at 25 ° C and 65% humidity:
* Dry to Touch: 30 Minutes
* Recoatable: 4 hours.

RECOMMENDED SYSTEM

■ INTERIOR

SYSTEM	NUMBER OF COATS
COLOPRIM or COLOFIX	1
COLENDUIT EXTRA B505 or SP88	2
COLOFONDO	1
SYLVIA	1

STORAGE

The product can be stored for up to 2 years in good storage conditions away from sunlight, it is nevertheless recommended to shake the product before use.

PACKAGING

2.5 Kg.

HEALTH & SAFETY

Health and safety information and precautions for use are detailed on the safety data sheet N°294 .

MINIMUM ORDER QUANTITY

Please contact our sales department .

Edition : August 2025 by Colorado 08/25 (DC28G).

N.B : The purpose of this technical data sheet is to provide information on the properties of our product. The information contained therein is based on our current knowledge of tests carried out with a constant concern for objectivity according to the conditions of use in accordance with standards or DTU in force; However, the information cannot replace an appropriate description and the state of the funds to be painted.
This descriptive technical sheet cancels and replaces any sheet relating to the same product. The above technical data does not imply acceptance of the guarantees. Close the pot tightly after use. Help preserve the environment by not disposing of waste in the drains or household waste. Please return your empty jar to a recycling center. For your unused product, please contact your local authorities for information on disposal and collection.

COLORADO is certified ISO 9001, ISO 14001, ISO 45001 and ISO 27001